



NIPPON VINILEX EASYWASH *Internal Emulsion*

Product Description:

Nippon Vinilex EasyWash is a modified acrylic emulsion paint with non-added lead and mercury which gives a very smooth classical matt finishing for interior walls. It is specially formulated with Low VOC and Alkyd Phenol Ethoxylate free for interior walls. This affordable medium premium range paint has good stain washability, good hiding power, easy application and durable.

Recommended Uses:

For decoration and protection of interior walls, ceilings, plaster, brickwork, hard and soft boards and asbestos.

Composition:

Pigments	: Mainly Titanium Dioxide, Iron Oxide, Carbon Black and Organic Pigments and Mineral Extender
Binder	: Modified acrylic Emulsion
Thinner	: Water

Properties:

Colour	: A wide range of colours. Please refer to colour card.
Appearance	: Classical Matt finish
Volume Solid	: 35%

Recommended no. of coats	: 2 coats
Recommended Dry Film Thickness Per Coat	: Around 30 µm (Actual thickness per coat is based on substrate condition)
Drying Time	
Touch Dry	: 15 minutes
Hard Dry	: 1 hour
Recoating Interval	: Minimum 2 hours
Theoretical Coverage at Recommended Dry Film Thickness	: 9 - 11 m ² per litre per coat (Actual coverage is dependent on substrate condition.) *

Application Methods:

- 1) Brush / Roller** : Dilute both the 1st and 2nd coats with 5 - 10% water.
- 2) Conventional Air Spray** : Dilute the paint with 20% water.
- 3) Airless Spray** : Dilute the paint with 5% water for the 1st and 2nd coats.
- Clean Up** : Clean up equipment with water immediately after use.

Surface Preparation:

Remove all loose, defective paint or powdery residues. Repair cracks, uneven surfaces with Nippon ACS Putty or suitable fillers. Smoothen the putty / filler areas with sandpaper. Surfaces to be painted must be cleaned thoroughly and dry, it must be free from dirt, grease and other foreign matters. Allow all surfaces to dry completely prior to painting. Avoid painting when the moisture content and alkalinity of the walls are still high. (Recommended painting specification requires the moisture content of the walls to be below 16% measured by protimeter and alkalinity of the walls to be below pH9.)

Previously Painted Surfaces

Remove all unstable paint film, loose chalk, dust and foreign matter. Make good any surface defects, clean off and dry. Spot prime with recommended WALL SEALER.

Recommended Paint System**Type of Substrate:**

FOR MASONRY (INTERNAL WALL AND CEILING)

Sequence	Product Name	No. of Coats
Sealer	NIPPON VINILEX 5200 WALL SEALER / NIPPON VINILEX 5500 WALL SEALER / NIPPON ACRYLIC 5170 WALL SEALER / NIPPON HI-BOND WALL SEALER	1
Finish	NIPPON VINILEX EASYWASH	2

Standard Packing : 1 litre and 5 litres

Safety, Health and Environmental Information:

Keep container tightly closed and keep out of reach of children or away from food and drink. Ensure good ventilation during application and drying. When applying paint, it is advisable to wear eye protection. In case of contact with eye, rinse with plenty of water immediately and seek medical advice. Remove splashes from skin by using soap or water. Paint must always be stored in a cool place. When transporting paint, care must be taken. Always keep container in a secure upright position.

Dispose off any paint waste in accordance with the appropriate Environmental Quality Regulations.

Note:

* Theoretical Coverage is based on a mathematical formula

$$\left[\frac{\text{Volume Solid \% x 10}}{\text{Dry Film Thickness}} \right] = \text{m}^2 / \text{lit} / \text{coat}$$

The dry paint film thickness and actual coverage does not consider LOSS FACTORS. Variables like porosity of substrate, application method, dilution ratio, opacity and so on will affect the loss factor and can vary from 30% - 50% or even more.

The above information is given to the best of our knowledge based on laboratory tests and practical experience.

However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself.

We reserve the right to alter the given data without prior notice.